

CLAIMS

1. Electrolytic process for plasma microarc oxidation for the purpose of obtaining a ceramic coating on the surface of a metal having semiconducting properties, such as aluminium, titanium, magnesium, hafnium, zirconium and their alloys, by a physico-chemical transformation reaction of the treated metal, characterized in that it consists in:
- 10 - immersing the metal workpiece (5) to be coated in an electrolytic bath (3) composed of an aqueous solution of an alkali metal hydroxide, such as potassium hydroxide or sodium hydroxide, and of an oxyacid salt of an alkali metal, the metal workpiece forming one of the electrodes; and
- 15 - applying a signal voltage of overall triangular waveform to the electrodes, that is to say a signal having at least a rising slope and a falling slope, with a form factor that can vary during the process, generating a current which is controlled in its intensity, its waveform and its ratio of positive intensity to negative intensity.
2. Process according to Claim 1, characterized in that the rising and falling slopes of the voltage signal are approximately symmetric.
- 25 3. Process according to Claim 1, characterized in that the rising and falling slopes of the voltage signal are asymmetric and have angles which vary during the electrolysis.
- 30 4. Process according to one of Claims 1 to 3, characterized in that it consists in making the value of the triangular voltage change between 300 and 600 Vrms during the process.
5. Process according to one of Claims 1 to 4, characterized in that it consists in making the frequency of the triangular signal vary between 100 and 400 Hz during the process.
- 35 6. Process according to one of Claims 1 to 5, characterized in that it consists in making the value

10018709-032702

7. Process according to the combination of Claims 1 to 6, characterized in that it consists in  
5 varying the various parameters, namely the form factor, the value of the potential, the frequency and the value of the current, independently during the process.

9. Process according to one of Claims 1 to 8,  
15 characterized in that it consists in separately  
controlling its waveforms and the electrical power  
values VI in the positive phase and/or in the negative  
phase.

25               - a module (10) for converting the sinusoidal  
AC signal delivered by the mains into a trapezoidal or  
sawtooth signal;

30           - a module (13) for varying the frequency in  
various types of cycle; and

35 11. Generator according to Claim 10, characterized in that it includes, at the output, an isolating transformer with series-connected capacitors in the primary or the secondary, in order to filter the DC component so as to prevent the magnetic circuit from

saturating, while introducing optimum operating safety in respect of electrical protection, with connection of one of the poles to earth.

12. Generator according to either of Claims 10 and  
5 11, characterized in that it is controlled by a PC-type processor (8) used to manage the various parameters during execution of the process.

20220909 10018709